

Auriga Polymers Inc.

Type 8597 Resin Provisional Data Sheet

Product Description

Type 8597 is a clear co-polyester resin than can be molded or extruded into a variety of products. Type 8597 is suitable for bicomponent fiber, nonwovens, APET film and clear molded parts. Type 8597 resin is supplied as a crystallized pellet.

Contact Auriga Polymers for specific process and design recommendations.

Property	Value	Test Method
Intrinsic Viscosity, dl/g	0.58 ± 0.02	1% Solution in Dichloroacetic Acid*
Carboxyl End Groups, meq/kg	50 Max.	Titration*
Diethylene glycol, wt%	1.5 Max.	Gas Chromatography*
Color L***	84 ± 4	Hunter Colorimeter
Color b***	-3 ± 4	Hunter Colorimeter
Melt Point, °C	229 ± 5.0	DSC
Chip Weight (g/20 chips)	0.50 ± 0.06	As measured
Moisture Content (wt %)	0.25 Max.***	Karl Fisher Titration

Determined by converting solution viscosity to intrinsic viscosity using an empirical correlation developed by Auriga Polymers Inc. equivalent to ASTM method D-4603

Product Data Sheet Disclaimer

This Product Data Sheet contains selected information about a specific Auriga Polymers Inc. product, or group of products. THIS PRODUCT DATA SHEET DOES NOT CONTAIN A COMPLETE STATEMENT OF, AND DOES NOT CONSTITUTE A REPRESENTATION, WARRANTY OR GUARANTY WITH REGARD TO, A PRODUCT'S CHARACTERISTICS, USES, QUALITY, MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR THE SUITABILITY, SAFETY, EFFICACY, HAZARDS OR HEALTH EFFECTS OF THE PRODUCT, WHETHER USED SINGULARLY OR IN COMBINATION WITH ANY OTHER PRODUCT, EXCEPT TO THE EXTENT REQUIRED BY RELEVANT LAWS AND REGULATIONS. Purchasers and users of the product are responsible for determining if the product is suitable for the intended use and that their workers and the general public are advised of any risks resulting from such use. Nothing contained in this Product Data Sheet shall be construed to modify any of the commercial terms pursuant to which the product was sold by Auriga Polymers Inc. including, but not limited to, terms and conditions addressing each party's respective rights and obligations with regard to warranties, remedies and indemnification.

^{**} Internal Auriga Polymers Inc. method

^{***} As manufactured